



Infrastructure Technologies

Gate 5, 2 Normanby Road Clayton VIC 3168, Australia

Telephone: 61 3 9545 2777 Web: <http://www.csiro.au>

Registered Testing Authority - CSIRO

23 November 2018

Our Ref. EN13 / 2582 03/0212

TEST REPORT No. 8180.2

Requested by: Decoline Pty Ltd
3/3363-3365 Pacific Highway
Slacks Creek,
QLD 4127

on (date): 6 September 2018

Manufacturer:
Product Desc.: Ocean

Sampling details:
Where: At customer premises
Date: 29 October 2018
By whom: Customer (delivered by courier)
How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 4 pages

SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

		Result	Class
AS 4586:2013 (Amendment No. 1)	Slip resistance classification of new pedestrian surface materials, Appendix D: OIL-WET INCLINING PLATFORM TEST METHOD Corrected mean overall acceptance angle:	13°	R 10

In order to interpret the classifications, please refer to Standards Australia Handbook 198, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



REPORT NO: 8180.2
ISSUE DATE: 23 November 2018
MANUFACTURER:
PRODUCT DESC: Ocean

Page 2 of 4

PHOTOS:



Top view



Close up



REPORT NO: 8180.2
ISSUE DATE: 23 November 2018
MANUFACTURER:
PRODUCT DESC: Ocean

Page 3 of 4

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

OIL-WET INCLINING PLATFORM TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS 4586:2013 (Appendix D) (Amendment No. 1)

Test Date: 23 November 2018

Location: Slip Resistance Laboratory Test conducted by: KH, DN

Sample Unfixed

Joint width: 0 mm

Surface structure: Smooth
 Profiled
 Structured

RESULTS

Corrected mean overall acceptance angle: 13 °

Displacement space: not tested

CLASSIFICATION: Slip Resistance Assessment Group:

R 10

Displacement Space Assessment Group:

-

Test shoe used: Leipzig V73-SP



Infrastructure Technologies

Gate 5, 2 Normanby Road Clayton VIC 3168, Australia

Telephone: 61 3 9545 2777 Web: <http://www.csiro.au>

REPORT NO: 8180.2
ISSUE DATE: 23 November 2018
MANUFACTURER:
PRODUCT DESC: Ocean

Page 4 of 4

Date and Place 23 November 2018, Clayton, Vic

Name, Title and Digital Signature:

A circular digital signature stamp. It features a greyish-blue background with the CSIRO logo (vertical bars and the word "CSIRO") in a lighter shade. Overlaid on this is a black, handwritten-style signature that appears to read "Khanh Ho".

KHANH HO
Technical Officer
Tel: 61 3 95452777
Email: Khanh.Ho@csiro.au
