

DECOLINE OCEAN

Sample description as provided by customer
VINYL PLANK Dimensions 228.6 mm x 1219.2 mm Thickness 5 mm

Order No. James

TEST METHOD: AS.ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by the Building Code of Australia (BCA) and National Construction Code 2015 (NCC) specifications C1.10. Sample conditioning as specified in BS EN 13238.2010.

Sample Submitted Date **May 2017** Test Date **12 May 2017** Total Thickness mm

Assembly System: DIRECT STICK (Details Below).

The floor covering was directly stuck to the substrate using Vinyl adhesive.

Substrate: Non-Combustible - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring. The Holding Torque on Specimen Frame was 2Nm.

The standard requires two Initial Tests be conducted on samples mounted in both Length and Width directions. Two further samples are then tested in whichever direction has the lowest Critical Radiant Flux.

Initial Tests: **Length** Direction Critical Radiant Flux **8.9 kW/m²**
Width Direction Critical Radiant Flux **8.7 kW/m²**

	Specimen Tests conducted in the Width Direction			
	Specimen #1	Specimen #2	Specimen #3	Mean
Critical Radiant Flux (kW/m ²)	8.7	8.6	8.7	8.7
Smoke Development Rate (%.min)	228	186	209	208

The values quoted below are as required by BCA and NCC Specification C1.10 Fire Hazard Properties (Floors). The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).


Mean Critical Radiant Flux 8.7 kW/m²

Mean Smoke Development Rate 208 %.min

Observations: The samples shrunk away from the heat source, ignited and burnt a relatively short distance.

AS.ISO 9239.1 Clause 9(o) The test results relate to the behaviour of the test specimens of a product under the particular conditions of the test; they are not intended to be the sole criterion for assessing the potential fire hazard of the product in use.

All information required for compliance with the BCA and NCC is given on this test report page.

 <small>ACCREDITED FOR TECHNICAL COMPETENCE</small>	M. B. Webb Technical Manager	
	DATE: 12 May 2017	
	Performance & Approvals Accreditation No. 15393 Accredited for compliance with ISO/IEC 17025.	

TIME FOR EACH SPECIMEN TO REACH EACH MARKER IN SECONDS

Specimen	50	60	110	160	210	260	310	360	410	460	510	560	610	660	710	760	810	860
1	215	217	399	508	793													
2	241	242	416	538	886													
3	239	240	385	493	752													

TESTS

BURNING CHARACTERISTICS

SMOKE PRODUCTION

Specimen	Burn Length (mm) at Flame Out/ Extinguishment	Time To Burn Out (s)	Maximum Light Attenuation (%)	Smoke Development Rate (%.min)
Initial Test: Length	230	881	38	242
Specimen Tests: Width				
1	242	953	36	228
2	249	1,026	38	186
3	241	972	41	209
Mean	244	984	38	208




M. B. Webb
Technical Manager

DATE: 12 May 2017

Performance and Approvals
Accreditation No. 15393
Accredited for compliance
with ISO/IEC 17025.

2004 04 09

3 July 2017